batteries

genesis NP

NP75-12
NP75-12FR

Sealed Rechargeable Lead-Acid Battery

12V, 77.5Ah

Specifications

- **NOMINAL VOLTAGE:** 12V
- **NOMINAL CAPACITY:**
  20 hr. rate of 3.87A to 10.5V 77.5Ah
  10 hr. rate of 7.18A to 10.5V 71.8Ah
  5 hr. rate of 13.6A to 10.2V 68.0Ah
  1 hr. rate of 55.4A to 9.60V 55.4Ah
- **WEIGHT (approx.):** 57 pounds (25.8kgs)
- **ENERGY DENSITY (20 hr. rate):** 1.45 WH/cubic inch (90 WH/liter)
- **SPECIFIC ENERGY (20 hr. rate):** 16 WH/pound (35 WH/kg)
- **INTERNAL RESISTANCE OF CHARGED BATTERY:** 5.5 milliohms (approx.)
- **MAXIMUM DISCHARGE CURRENT WITH STANDARD TERMINALS:** 150 amperes
- **MAXIMUM SHORT-DURATION DISCHARGE CURRENT:** 500 amperes
- **OPERATING TEMPERATURE RANGE:**
  CHARGE 5°F to 122°F (-15°C to 50°C)
  DISCHARGE -4°F to 140°F (-20°C to 60°C)
- **CHARGE RETENTION (shelf life) at 68°F (20°C):**
  1 month 97%
  3 months 91%
  6 months 85%
- **LIFE EXPECTANCY:**
  STANDBY USE 3 to 5 years
  CYCLE USE (approx.):
  100% depth of discharge 250 cycles
  50% depth of discharge 550 cycles
  30% depth of discharge 1200 cycles
- **SEALED CONSTRUCTION:** Can be operated in any position without leakage.
- **STANDARD TERMINAL:** Universal or options in terminal diagram
- **HOUSING MATERIAL:** PP Resin
- **OPTIONAL:** Container and cover made from Flame Retardant PP (UL94-V0/L.O.I.>28%)

Terminal

Standard



U Positive Terminal



U Negative Terminal

Terminal height above cover

Terminal Type	NP75-12 mm	NP75-12 ins
B	3.3	0.13
NB	21.1	0.83
MJ	26.9	1.06
AP	21.1	0.83
MG	36.3	1.43
U	21.1	0.83

Optional



MG Positive

MG Negative

Automotive Type AP Positive



Automotive Type AP Negative



NB Terminal



B Terminal



MJ Terminal

Note:
Dimensions are in inches (mm)
Tolerances are ± 0.04 in. (±1mm) and ± 0.08 in. (± 2mm) for height dimensions.

Dimensions



DIMENSIONS: INCHES (MM)

RECOGNIZED BY UL, File No. MH 14328

EnerSys™
Power/Full Solutions™

Publication No: US-NP75-12-01 • May 2003

DISCHARGE CHARACTERISTIC CURVES AT 25°C (77°F)



TEMPERATURE EFFECTS IN RELATION TO BATTERY CAPACITY



SELF DISCHARGE CHARACTERISTICS



OPEN CIRCUIT VOLTAGE VS REMAINING CAPACITY



CYCLE SERVICE LIFE IN RELATION TO DEPTH OF DISCHARGE



FLOAT SERVICE LIFE



When the battery will be used by current in excess of 3C, consult with EnerSys, Inc. prior to use.

CHARGING METHODS (At 20ºC)

Cycle use: Maximum charging current 0.25C
Charging voltage 14.4 to 15.0V

Standby use: Float charging voltage 13.50 to 13.80V

CAUTION •Avoid short circuit
•Do not charge in a sealed container.

Publication No: US-NP75-12-01 • May 2003

EnerSys Inc.
P.O. Box 14145
Reading, PA 19612-4145
USA
Tel:+1-610-208-1991
+1-800-538-3627

EnerSys EMEA
Brussels, Belgium
Tel:+32 (0)2 247 94 47
EnerSys Asia
Guangdong, China
Tel:+86 755 2689 3639

www.enersysinc.com

Represented by:

GO batteries

Printed in USA